

GOLI VODIČI

Cu VODIČ		
SIROVINA	Bakar (Cu)	čistoća 99,99%
NORMA	ASTM	B 49
PROIZVODNE DIMENZIJE	Maksimalni odnos $b_1 : s_1$	10 : 1
	Minimalni presjek (mm^2)	10
	Maksimalni presjek (mm^2)	150
PROIZVODNE DIMENZIJE	Okrugla žica	$\geq 0,300\text{mm}$
NORMA	IEC	60317-0-2 60317-0-1
VODLJIVOST	kod 20°C	$\geq 58\text{m}/\Omega\text{mm}^2$
SPECIFIČNI OTPOR	kod 20°C	$\leq 0,017$ $\Omega\text{mm}^2/\text{m}$

